

# ST 95

## STRUCTURAL SPRINT™

- Good balance of mechanical properties
- Excellent laminate quality
- Extremely low void content
- Drape-able and conformable
- Good tack
- Fast layup
- No de-bulk necessary between plies
- Variable cure temperature 85-120°C (185-257°F)
- DNV-GL Certified Formats Available


### INTRODUCTION

The patent-approved ST 95 Structural SPRINT™ is a moulding material that consists of two layers of carbon or glass reinforcement either side of a precast, pre-catalysed resin film. The material therefore has the appearance of dry reinforcement that has resin concealed at its centre. Carbon and Glass SPRINT™ are available in woven or unidirectional fabric skewed to  $\pm 45^\circ$  angles in a range of weights and fabric formats with a light tack film on one side to aid mould placement.

ST 95 is a toughened hot-melt, epoxy resin that offers an extremely good balance of mechanical properties. It has been formulated to maximise the out-life of SPRINT™ products at room temperature. It is ideal for structural components where improved impact performance and resistance to resin micro-cracking is desired.

ST 95 has a flexible cure envelope from 10 hours at 85°C (185°F) to 1 hour at 120°C (248°F). This makes it suitable for use in regular part production as well as for the development of trial components. The material is highly drape-able and has been designed for simple vacuum bag processing.

Structural SPRINT™ ST 95 can be used in the manufacture of a vast range of structural applications such as chassis, bulkheads, hulls and decks, for automotive and marine markets, as well as many other industrial applications.




## INSTRUCTIONS FOR USE

1. The moulding surface must first be treated with a release agent. If a Surface Film is required, this should be applied directly to the tool face prior to the lay-up of the SPRINT™. Please refer to Processing Notes for application details.

The required number of plies of SPRINT™ are then placed on to the tool face. A thermocouple may be inserted into the lay-up outside the net trim line. Dry glass tows should be inserted between plies of SPRINT™ to provide an air evacuation path out of the laminate. The second end of the tow should be made available for contact with the breather.

2. If required, a peel ply, pre-impregnated or dry, can be applied over the top of the laminate stack. Note that for good secondary bonding of a peel-plyed surface of a laminate, a nylon peel ply such as Tygavac Stitch Ply A, is strongly recommended. The peel ply is covered entirely with a non-perforated release film such as Tygavac WL3600 or a low bleed release film, such as WL3600RP2. The release film is then covered with breather material, such as Tygavac Econoweave 44W, so that it extends over the release film in all directions and contacts the dry glass strands.



Typical processing diagram showing two SPRINT™ layers

3. Once the lay-up is complete, a vacuum bag is installed by standard techniques. At least two vacuum stems should be inserted through the bag, one connecting to the vacuum source and the other, at a point on the part furthest from the source, to a calibrated vacuum gauge. The major benefit of SPRINT™ is that it enables all of the air to be removed from the laminate prior to fibre wet out and resin cure. It is recommended that a vacuum is applied at ambient temperature prior to cure, to fully evaluate the laminate stack. This should be held for between 5 minutes and 1 hour, depending upon the size and thickness of the component. Full vacuum is then maintained throughout the cure.

4. Cure the laminate in accordance with the specification given later in this datasheet.

PLEASE NOTE:

If processing SPRINT™ with foam cores, additional resin will be required in order to provide good adhesion and fill any cuts or grooves present in the core.

The additional resin can be provided by using SA80 adhesive film between the laminate and core. Gurit can also provide SPRINT™ with a higher resin content which could be used as an alternative or in conjunction with SA80.

Core type, density, thickness, cut patterns and panel curvature will all have an effect on the additional resin requirement. Representative panels should be made to establish that sufficient additional resin has been used for the core type.

Further advice can be found in the SPRINT™ Processing Notes or by contacting Gurit Technical Support.

## CURING SCHEDULE

### CURE ENVELOPE AND CURED PROPERTIES


Structural SPRINT™ ST 95 has a relatively flexible cure envelope. The minimum cure is 10 hours 85°C (185°F) and rapid cure is 1 hour at 120°C (248°F). Other cure temperatures and times are given in the Working Properties section.

Structural SPRINT™ ST 95 works by first applying a vacuum to the laminate stack to remove all air. It is recommended that an ambient vacuum is applied prior to cure, to fully evacuate the laminate stack. The temperature is then increased so that the matrix resin reduces in viscosity and wets the evacuated reinforcement within the laminate. A dwell can be used at the "infusion" temperature to ensure good laminate quality. The temperature is then further increased to cause the matrix resin to cross-link and is then held at the cure temperature until the cross linking process is complete. Once this is achieved heating is removed so that the temperature is reduced under natural cooling. The vacuum must be maintained throughout the cure until the part has been cooled to 40°C (104°F).

### TYPICAL CURE PROFILES

The successful use of these cure schedules will depend on part size laminate construction. Heat up rate and dwell periods need to be tailored to take consideration of oven capacity, thermal mass of tool, laminate construction etc. Data in the minimum cure temperature table on the next page is based on laminate temperatures, air temperatures may need to be higher. It is recommended that Gurit is contracted for further advice before utilising any of the suggested cure cycles.

#### Fast Cure Cycle Structural SPRINT™ ST 95:



## PRODUCT INFORMATION

ST 95 structural SPRINT™ is available in carbon and glass, with a range of weights on a range of fabric and fibre combinations. Products are available with a standard resin content (40-42% by wt) and extra resin for core bonding (ranging from 47-50% by wt). The product formats listed to the right also benefit from 3<sup>rd</sup> Party Certification and specific details can be found by downloading the certificate from [guriit.com](http://guriit.com).

### COMPATIBLE SURFACE FILMS


SPRINT™ can be used in combination with a variety of Gurit surfacing materials, suitable for many different applications. Please see price list for latest product information.

### PREPREG PROPERTIES

#### RHEOLOGY DATA

ST 95 resin viscosity profile conducted at 1°C (1.8°F)/minute.

| PROPERTY                         | VALUE     |        |
|----------------------------------|-----------|--------|
| Minimum Viscosity                | 2.44 Pa.s | 24.4 P |
| Temperature at Minimum Viscosity | 103 °C    | 217 °F |



| PRODUCT DESCRIPTION                           | STATUS              | CERTIFICATION         |
|---|---------------------|-----------------------|
| ST 95 2 plies of RE301 30-55% resin content   | Renewal in progress | DNV-GL W/P 1430023 HH |
| ST 95 2 plies of WRE581T 30-55% resin content | Renewal in progress | DNV-GL W/P 1430023 HH |
| ST 95 2 plies of RC303T 30-55% resin content  | Renewal in progress | DNV-GL W/P 1430019 HH |

### COMPATIBLE ADHESIVE FILMS

Gurit have a range of SA 80 adhesive films which can be used with all SPRINT™ materials. These are supplied with a supporting medium in 250g and 400g film weights.

#### TRANSPORT & STORAGE

When stored sealed & out of direct sunlight.

| STORAGE TEMP |         | UNIT   | VALUE |
|--------------|---------|--------|-------|
| -18°C        | 0°F     | months | 24    |
| +18-22°C     | 64-72°F | days   | 21    |

The self-impregnation of the SPRINT™ can compromise its ability to generate high quality laminates as the air breathing properties decrease after a certain length of time at ambient temperature. Self-impregnation will increase the tack and reduce the drape of the material. While self-impregnation will vary from product to product, most SPRINT™ materials stored at ambient temperatures will self-impregnate within approximately two weeks. It is recommended that ambient temperature storage is below 22°C (71°F) as higher storage temperatures will induce premature self-impregnation. All SPRINT™ materials should be stored in a freezer when not in use to maximise their useable life, since the low temperature reduces the reaction of resin and catalyst to virtually zero. However, even at -18°C (0°F), the temperature of most freezers, some reaction will still occur. In most cases after some years, the material will become unworkable. To avoid condensation on the rolls allow to reach room temperature before unwrapping.

### HEALTH AND SAFETY

Please refer to product SDS for up to date information specific to this product.

### MINIMUM CURE TIME & TEMPERATURE

ST 95 SPRINT™ using vacuum bag processing with recommended minimum cure of 10 hours at 85°C (185°F)

| PROPERTY                  | ULTRA SLOW CURE CYCLE       | STANDARD CURE CYCLE    | FAST CURE CYCLE                          | TEST STANDARD |
|---------------------------|-----------------------------|------------------------|--|---------------|
| Processing Method         | Vacuum Bag                  |                        |  |               |
| Typical Ramp Rate         | 0.3°C (0.5°F) per minute    | 1°C (1.8°F) per minute | 2°C (3.6°F) per minute                   | -             |
| Cure Temperature          | 78°C (172°F)                | 85 °C (185°F)          | 75°C (167°F)                             | -             |
| Cure Dwell Time           | 120 (min)                   | 600 (min)              | 0.5°C (0.9°F) per minute to 90°C (194°F) | -             |
| Post-Cure Temperature     | 85°C (185°F)                | -                      | 120°C (248°F)                            | -             |
| Post-Cure Dwell Time      | 600 (min)                   | -                      | 60 (min)                                 | -             |
| Cure Pressure             | -1 (bar)                    |                        |  | -             |
| Dry Tg <sub>1</sub> (DMA) | 100 to 105°C (212 to 221°F) |                        | 123°C (253°F)                            | ASTM D7028    |

\* It is recommended that laminate temperatures are monitored throughout the cure. 0.3°C (0.5°F)/min should be considered the minimum ramp rate.

## LAMINATE PROPERTIES

Where possible, properties presented are multiple batch data and witnessed by a third party surveyor on a standard fibre type. Customers with specific requirements should contact Gurit technical support who can recommend suitable fibres and formats.

## CURED RESIN PROPERTIES

Resin cast oven cured using standard processing techniques and standard cure of 10 hours at 85°C (185°F)

| PROPERTY             | SYMBOL     | 10 HOURS @ 85 °C (185°F) |          | TEST STANDARD |
|----------------------|------------|--------------------------|----------|---------------|
| Tensile Strength     | $\sigma_T$ | 79 MPa                   | 11.5 ksi | ISO 527-2     |
| Tensile Modulus      | $E_T$      | 3.3 GPa                  | 0.48 Msi | ISO 527-2     |
| Compressive Strength | $\sigma_C$ | 127 MPa                  | 18.4 ksi | ISO 604       |
| Compressive Modulus  | $E_C$      | 3.5 GPa                  | 0.51 Msi | ISO 604       |

## WOVEN LAMINATE PROPERTIES

Cured using standard processing techniques and standard cure of 10 hours at 85°C (185°F). Where test directions are provided they are with respect to the warp direction of the roll.

| PROPERTY                 | SYMBOL   | UNIT | RC303T / ST95 / RC303T | RE301 / ST95 / RE301 | WRE581T / ST95 / WRE581T | TEST STANDARD         |
|--------------------------|----------|------|------------------------|----------------------|--------------------------|-----------------------|
| Resin Content            | -        | %    | 51                     | 46                   | 41                       | ASTM D 3171 Method II |
| Cured Ply Thickness      | -        | mm   | 0.81                   | 0.63                 | 1.08                     | ASTM D792             |
| Fibre Volume Fraction    | -        | %    | 41.0                   | 36.6                 | 41.3                     | ASTM D 3171 Method II |
| 0° Tensile Strength*     | $X_T$    | MPa  | 987                    | 621                  | 607                      | ISO 527-4             |
| 0° Tensile Modulus*      | $E_t$    | GPa  | 58                     | 31                   | 28                       | ISO 527-4             |
| 0° Compressive Strength* | $X_C$    | MPa  | 610                    | 678                  | 600                      | SACMA SRM1-94         |
| 0° Compressive Modulus*  | $E_c$    | GPa  | 60                     | 32                   | 31                       | SACMA SRM1-94         |
| ILSS                     | $\tau_M$ | MPa  | 59                     | 58                   | 53                       | ISO 14130             |

\*Normalised to 55% fibre volume fraction

## MULTIAXIAL LAMINATE PROPERTIES

Cured using standard processing techniques and standard cure of 10 hours at 85°C (185°F). Where test directions are provided they are with respect to the warp direction of the roll.

| PROPERTY                   | SYMBOL   | UNIT | +45° 300GSM / ST95 / -45° 300GSM SKEWED CARBON BIAX | TEST STANDARD         |
|----------------------------|----------|------|---|-----------------------|
| Resin Content              | -        | %    | 42  | ASTM D 3171 Method II |
| Cured Ply Thickness        | -        | mm   | 0.77  | ASTM D792             |
| Fibre Volume Fraction      | -        | %    | 43.4  | ASTM D 3171 Method II |
| ±45° Tensile Strength*     | $X_T$    | MPa  | 1040  | ISO 527-4             |
| ±45° Tensile Modulus*      | $E_t$    | GPa  | 57  | ISO 527-4             |
| ±45° Compressive Strength* | $X_C$    | MPa  | 649   | SACMA SRM1-94         |
| ±45° Compressive Modulus*  | $E_c$    | GPa  | 63  | SACMA SRM1-94         |
| ±45° ILSS                  | $\tau_M$ | MPa  | 46  | ISO 14130             |

\*Normalised to 55% fibre volume fraction

## NOTICE

All advice, instruction or recommendation is given in good faith but the selling Gurit entity (the Company) only warrants that advice in writing is given with reasonable skill and care. No further duty or responsibility is accepted by the Company. All advice is given subject to the terms and conditions of sale (the Conditions) which are available on request from the Company or may be viewed at Gurit's Website: [www.gurit.com/terms-and-conditions.aspx](http://www.gurit.com/terms-and-conditions.aspx)

The Company strongly recommends that Customers make test panels in the final process conditions and conduct appropriate testing of any goods or materials supplied by the Company prior to final use to ensure that they are suitable for the Customer's planned application. Such testing should include testing under conditions as close as possible to those to which the final component may be subjected. The Company specifically excludes any warranty of fitness for purpose of the goods other than as set out in writing by the Company. Due to the varied nature of end-use applications, the Company does, in particular, not warrant that the test panels in the final process conditions and/or the final component pass any fire standards.

The Company reserves the right to change specifications and prices without notice and Customers should satisfy themselves that information relied on by the Customer is that which is currently published by the Company on its website. Any queries may be addressed to the Technical Services Department.

Gurit is continuously reviewing and updating literature. Please ensure that you have the current version by contacting your sales contact and quoting the revision number in the bottom left-hand corner of this page.

## TECHNICAL CONTACT INFORMATION

For all other enquiries such as technical queries:

Telephone + 44 1983 828000 (08:30 – 17:00 GMT)  
Email [technical.support@gurit.com](mailto:technical.support@gurit.com)

## 24-HOUR CHEMICAL EMERGENCY NUMBER

For advice on chemical emergencies, spillages, fires or exposures:

Europe +44 1273 289451  
Americas +1 646 844 7309  
APAC +65 3158 1412

**All trademarks used or mentioned in this document are protected by law.**

**E** [customer.support@gurit.com](mailto:customer.support@gurit.com)

**W** [www.gurit.com](http://www.gurit.com)