

PH 860

HI-HO COSMETIC PHENOLIC PREPREG

- ↗ Crush-Core prepreg for short curing cycles
- ↗ Self-adhesive resin system for sandwich panel application
- ↗ Non-halogenated resin formulation
- ↗ Excellent FST behaviour
- ↗ Very good surface quality
- ↗ Amber colour after cure for high varnish and decorative film coverage
- ↗ Long shelf and shop life

INTRODUCTION

PH 860 phenolic resin is a halogen-free and self-adhesive modified phenolic system designed for very good surface-quality and excellent heat-release and smoke-density properties.

After cure, the PH 860 resin shows an amber colour appearance for high varnish and decorative film coverage. Both monolithic and sandwich structures can be easily manufactured with this prepreg. The curing can be performed by press, vacuum and autoclave moulding with a pressure of at least 0.7 bar / 10 psi.

PH 860 prepreg is especially suitable for curing of sandwich panels in an isothermal press cycle without heating and cooling stages. This hot-in/hot-out (HI-HO) crush-core process is a fast manufacturing method with curing-cycles less than 10 minutes and is mainly used to produce curved interior sandwich panels such as sidewalls or ceilings.

The prepreg material is suitable for monolithic and sandwich structures:

- ↗ Aviation and aerospace industries
- ↗ Marine and automotive applications
- ↗ Rail industries

PRODUCT INFORMATION

PH 860 phenolic prepreg is available in a range of product formats. Please consult your local sales contact for further information. Full contact details can be found at www.gurit.com.

PROPERTY	PHG860-68-40	TEST STANDARD
Resin	Phenolic	-
Prepreg Weight	510 ± 30 g/m ²	QVA-Z10-46-08
Volatile	6.5 ± 1.5 %	QVA-Z10-46-11
Resin Flow	> 20 %	QVA-Z10-46-33
Tackiness	T0 / None	-
Fibre Material	E-glass	-
Fabric Weight	296 g/m ² ± 5 %	EN 2331
Weave Style	8H Satin	-
Service Temperature (Cured State)	-55°C to +80°C (-67°F to 176°F)	-
Resin Content	40 ± 3 %	QVA-Z10-46-27
Typical Roll Length	50 m / 57 yd	-
Typical Roll Width	1.27 m / 50 in	-

PREPREG PROPERTIES

TRANSPORT & STORAGE

When stored sealed & out of direct sunlight.

All prepreg materials should be stored in a freezer when not in use to maximise their useable life, since the low temperature reduces the reaction of resin and catalyst to virtually zero. However, even at -18°C (0°F), the temperature of most freezers, some reaction will still occur. In most cases after some years, the material will become unworkable.

STORAGE TEMP		UNIT	VALUE
-18°C	0°F	months	6
+21°C	+70°F	days	15

HEALTH AND SAFETY

Please refer to product SDS for up to date information specific to this product.

QUALIFICATIONS / FIRE PERFORMANCE

PRODUCT	QUALIFICATIONS	FIRE PERFORMANCE
PHG860-68-40	→ 75-T-2-0410-2-1 (Airbus)	→ ABD 0031 → FAR 25.853 Flame Test (self-extinguishing)

CURING CONDITIONS

PROPERTY	CRUSH CORE	STANDARD CYCLE	TEST STANDARD
Recommended curing process	Press	Press / Autoclave	-
Spec. Pressure	12.5 bar / 182 psi	12.5 bar / 182 psi	-
Heat-up	None (hot-in)	3°C/min	-
Temperature	160°C / 320°F	160°C / 320°F	-
Cure Time	10 min	15 min	-
Cool-down	None (hot-out)	5°C/min	-
Remove material at	160°C / 320°F	80°C / 176°F	-

LAMINATE PROPERTIES

All data presented in this datasheet is based on the mechanical testing of a single batch of material.

MECHANICAL PROPERTIES AT ROOM TEMPERATURE (21°C / 70°F)

PROPERTY	SYMBOL	PHG860-68-40		TEST STANDARD
0° Flexural Strength	X _F	520 MPa	75 Ksi	ISO 178
0° Flexural Modulus	E _{F11}	18 GPa	2.61 Msi	ISO 178
0° Interlaminar Tensile Shear Strength	X _{ILTSS}	21 MPa	3.04 Ksi	AITM 1.0019
0° Interlaminar Shear Strength	X _{ILSS}	-	-	EN 2563
Climbing Drum Peel*	σ _{PEEL}	100 N/75 mm		EN 2243-3
Bending Load*	F _{BENDING}	800 N		AITM 1.0018
Glass Transition Temperature	T _g	-	-	ISO 6721 (DMA)

*sandwich structure: 2 plies per side; core 3.2-48kg/m³ 9.4mm (honeycomb)

MECHANICAL PROPERTIES AT 80°C (176°F)

PROPERTY	SYMBOL	PHG860-68-40		TEST STANDARD
0° Interlaminar Tensile Shear Strength	X _{ILTSS}	18 MPa	2.61 Ksi	AITM 1.0019

BURN BEHAVIOUR

PROPERTY	PHG860-68-40	TEST STANDARD
Flammability vertical, 60s flaming – Burn length	< 60 mm	AITM 2.0002A
Flammability vertical, 60s flaming – After flame time	0 s	AITM 2.0002A
Flammability vertical, 60s flaming – After flame time of drips	0 s	AITM 2.0002A
Max. specific optical smoke density within 4 min (flaming mode)	10 Ds	AITM 2.0007A
Heat Release	35 kW/m ²	AITM 2.0006
Heat Release Rate	45 kW.min/m ²	AITM 2.0006

NOTICE

All advice, instruction or recommendation is given in good faith but the Company only warrants that advice in writing is given with reasonable skill and care. No further duty or responsibility is accepted by the Company. All advice is given subject to the terms and conditions of sale (the Conditions) which are available on request from the Company or may be viewed at the Company's Website: www.gurit.com/terms-and-conditions.aspx.

The Company strongly recommends that Customers make test panels and conduct appropriate testing of any goods or materials supplied by the Company to ensure that they are suitable for the Customer's planned application. Such testing should include testing under conditions as close as possible to those to which the final component may be subjected. The Company specifically excludes any warranty of fitness for purpose of the goods other than as set out in writing by the Company. The Company reserves the right to change specifications and prices without notice and Customers should satisfy themselves that information relied on by the Customer is that which is currently published by the Company on its website. Any queries may be addressed to the Technical Services Department.

Gurit are continuously reviewing and updating literature. Please ensure that you have the current version, by contacting Gurit Marketing Communications or your sales contact and quoting the revision number in the bottom right-hand corner of this page.

E contact@gurit.com

W www.gurit.com