

# AMPREG™ 3X HIGH TG HARDENER

## AMPREG™ 30 & 31 EPOXY WET LAMINATING SYSTEMS

- Low and high viscosity resins to suite different applications
- Clear Ampreg™ 30 resin ideal for clear laminating applications
- Ampreg™ 31 resin viscosity optimised for drainage resistance
- Excellent cure progression and high Tg after suitable post-cure
- Tough resin matrix giving good laminate mechanical properties
- Formulated with Gurit LRT (Light Reflective Technology) as standard

### INTRODUCTION

**Ampreg™ 3X Series High Tg hardener has been optimised for the manufacture of large composite structures using hand layup and vacuum bagging techniques for use with Ampreg™ 30 and Ampreg™ 31 resins.**

The relatively low initial mixed viscosity of Ampreg™ 30 allows easy wetout of heavyweight reinforcements. Ampreg™ 30 resin combined with Ampreg™ 3X Series high Tg hardener is a clear mixed system with a high Tg potential after a suitable post-cure. When combined with a suitable lacquer, this makes it ideal for the manufacture of clear coated carbon components that may be exposed to high ambient temperatures during service.

The viscosity of Ampreg™ 31 has been optimised for good fabric wet-out whilst maintaining good drainage resistance for application on vertical surfaces. Ampreg™ 31 resin combined with Ampreg™ 3X Series high Tg hardener has been designed to give excellent mechanical and thermal properties with a high Tg potential after a suitable post-cure.

The unique formulation offers improved health & safety through Light Reflective Technology which in conjunction with a UV light-source can detect droplets as small as 1mm for easy identification of contamination to improve industrial hygiene.

SYSTEM PROPERTIES AT 20°C		MIXED VISCOSITY*	150g POT-LIFE*	EARLIEST TIME TO APPLY VACUUM*	LATEST TIME TO APPLY VACUUM*	EARLIEST DEMOULD TIME*	PAGE
High Tg Hardener	Product Information, Instructions for Use and Health & Safety						2
	Ampreg™ 30 Resin	820 cP	8½ hour	7 ¼ hours	9 ¼ hours	60 hours	4
	Ampreg™ 31 Resin	1110 cP	5 ¾ hour	4 ¾ hours	6 ¾ hours	30 hours	5

*\*working time properties are highly subjective to ambient conditions and should be used as an approximate guideline for all Ampreg™ systems at 20°C. Please refer to the corresponding page of this document for specific testing methods used.*

## PRODUCT INFORMATION

### AVAILABILITY

The product is available in a number of formats please contact your local customer support representative for more information.

### TRANSPORT & STORAGE

The resin and hardeners should be kept in securely closed containers during transport and storage. Any accidental spillage should be soaked up with sand, sawdust, cotton waste or any other absorbent material. The area should then be washed clean (see appropriate Safety Data Sheet).

COMPONENT	UNITS	10 – 25°C
Ampreg™ 30 & Ampreg™ 31 Resin	months	24
Ampreg™ 3X High Tg Hardener	months	24

Adequate long term storage conditions will result in a shelf life of 2 years for both the resin and hardeners. Storage should be in a warm dry place out of direct sunlight and protected from frost. The storage temperature should be kept constant between 10°C and 25°C, cyclic fluctuations in temperature can cause crystallization. Containers should be firmly closed. Hardeners, in particular, will suffer serious degradation if left exposed to air.

## INSTRUCTIONS FOR USE

The product is optimised for use lower temperatures the product thickens and may become unworkable. At higher temperatures working times will be significantly reduced. Maximum relative humidity for use is 70%.

### MOULD RELEASE

Smooth metal and GFRP mould tests have shown that suitable release can be obtained by use of 5-6 waxings of a carnauba based wax e.g. Polywax. Use PVA for less well prepared or more complex surfaces. The highest quality surface can normally be generated by using semi-permanent release systems like TR 920 (TR Industries) or PMR EZ (Chemlease).

Before the application of the release agent onto a new mould it should be sealed and primed, this is also true if an old mould have had its release agents stripped and a new system applied. It is suggested that a complete system is purchased from a single manufacture to ensure there are no compatibility issues. A low VOC (Volatile Organic Chemical) option is water based systems like chemlease 5051W or 5016W which will not generate class A surface finish but will help to reduce VOC release in moulding areas. Whichever mould release is proposed it is recommended that a test laminate is laid up under production conditions and time scales, in order to ensure an adequate and effective part release.

### MIXING AND HANDLING

Accurate measurement and thorough mixing are essential when using this system, and any deviation from the prescribed mix ratios will seriously degrade the physical properties of the cured system. The resin and hardener must be stirred well for two minutes or more, with particular attention being paid to the sides and bottom of the container. As soon as the material is mixed the reaction begins. This reaction produces heat (exothermic), which will in turn accelerate the reaction. If this mixed material is left in a confined mixing vessel the heat cannot disperse and the reaction will become uncontrollable.

### APPLICATION

The mixed system is usually applied by foam roller from a roller tray. Accurate fibre volume fractions can be obtained by applying a known weight of mixed resin / hardener to each fabric / fibre layer. As a general rule of thumb, resin weight per square metre must be no more than, and preferably less than, the area weight of the fabric being wet out. If the laminate is particularly thick, it is recommended that slower hardeners are used for laminating the first layers and faster hardeners in the later layers. In this way the whole thickness laid down remains workable for approximately the same time. For further advice, please contact Gurit Technical Support.

### BONDING TECHNIQUES & PEEL PLY

It is recommended to use nylon peel ply for any secondary bonding applications. Peel Ply is typically used on laminate surfaces which need to be left to cure or partially cure before further laminating or bonding operations. The peel ply serves two functions - preventing the surface from becoming contaminated and / or damaged, and providing a 'textured' surface that can reduce the level of preparation required for the secondary laminating or bonding operations. After curing and just prior to bonding, the Peel Ply is stripped off leaving a clean, dust and grease free surface, with an already 'textured' surface which makes the 'keying' process less time consuming. Gurit recommends the use of its Stitch Ply A peel ply, or suitable Tygavac product. Any proposed peel ply should be tested prior to use to ensure that it not only releases adequately from the laminated surface but also does not leave any residues behind which may impair adhesion. If in doubt please contact Gurit Technical Support.

### VACUUM BAG TECHNIQUES

Consolidation of the laminate can be obtained either by hand using paddle rollers or by vacuum or pressure bags. A typical vacuum bag arrangement is shown in figure 1. It is important when using high vacuums and using the slower hardeners that vacuum is not applied until at least 50% into the mixed system working time, as applying the vacuum earlier may result in excessive resin flow and resin starved laminates. For advice on effective vacuum bag consolidation, please contact Gurit Technical Support.




Figure 1

## CURING SCHEDULE

---

### AMBIENT TEMPERATURE CURE

The system has been developed to provide good mechanical properties after an ambient only cure. The minimum recommended cure temperature is 18°C. Excellent mechanical/thermal properties can be achieved after a slightly elevated temperature post-cure. An initial cure of at least 48 hours (with slow hardener) or 16 hours (with fast hardener) at 18°C is recommended before demoulding.

When using the Slow, Extra Slow or High Tg Hardeners exclusively, an elevated temperature postcure is strongly recommended.

### ELEVATED TEMPERATURE CURE

Post curing the laminate will greatly increase mechanical/thermal properties. The system will achieve similar properties with a cure of 5 hours at 70 - 80°C or 16 hours at 50°C. The latter temperature is easily achievable with low cost heating and insulation techniques.

The post cure need not be carried out immediately after laminating. It is possible to assemble several composite components and post-cure the entire assembly together. It is recommended, however, that elevated temperature curing should be completed before any further painting / finishing operations. Furthermore, care should be taken to adequately support the laminate if it is to be post cured after demoulding, and the laminate must be allowed to cool before the support is removed.

When postcuring it is recommended to use a ramp rate of 10°C/hour when heating from ambient to the postcure temperature, to ensure that the thermal performance of the laminate stays ahead of the oven temperature. Higher ramp rates may result in the resin softening and distortion of the part.

## HEALTH AND SAFETY

---

The following points must be considered:

1. Skin contact must be avoided by wearing protective gloves. Gurit recommends the use of disposable nitrile gloves for most applications. The use of barrier creams is not recommended, but to preserve skin condition a moisturising cream should be used after washing.
2. Overalls or other protective clothing should be worn when mixing, laminating or sanding. Contaminated work clothes should be thoroughly cleaned before re-use.
3. Eye protection should be worn if there is a risk of resin, hardener, solvent or dust entering the eyes. If this occurs flush the eye with water for 15 minutes, holding the eyelid open, and seek medical attention.
4. Ensure adequate ventilation in work areas. Respiratory protection should be worn if there is insufficient ventilation. Solvent vapours should not be inhaled as they can cause dizziness, headaches, loss of consciousness and can have long term health effects.
5. If the skin becomes contaminated, then the area must be immediately cleansed. The use of resin-removing cleansers is recommended. To finish, wash with soap and warm water. The use of solvents on the skin to remove resins etc must be avoided.  
Washing should be part of routine practice:
  - before eating or drinking
  - before smoking
  - before using the lavatory
  - after finishing work
6. The inhalation of sanding dust should be avoided and if it settles on the skin then it should be washed off. After more extensive sanding operations a shower/bath and hair wash is advised.

### APPLICABLE RISK & SAFETY PHRASES

Gurit produces a separate full Safety Data Sheet for all hazardous products. Please ensure that you have the correct SDS to hand for the materials you are using before commencing work.

## AMPREG™ 30 RESIN & AMPREG™ 3X HIGH TG HARDENER

This 1 page product summary is intended for use in conjunction with further advice provided under the Instructions for Use section. All data has been generated from typical production material and does not constitute a product specification.

### MIXING AND HANDLING

PROPERTY	UNITS	AMPREG™ 30 RESIN	HIGH TG HARDENER	MIXED SYSTEM	TEST METHOD
Colour	-	Colourless	Colourless	Colourless	-
Mix ratio by weight	Parts by weight	100	29	-	-
Mix ratio by volume	Parts by volume	100	34	-	-
Density at 21 °C	g/cm <sup>3</sup>	1.14	0.96	1.09	ISO 1183-1B

### COMPONENT & MIXED SYSTEM PROPERTIES\*

PROPERTY	UNITS	15°C	20°C	25°C	30°C	TEST METHOD
Ampreg™ 30 Resin Viscosity	cP	5200 - 5600	2400 - 2800	1300 - 1700	600 - 1000	-
Ampreg™ 3X High Tg Hardener Viscosity	cP	110	80	60	40	-
Initial Mixed System Viscosity	cP	-	820	-	-	-
Pot-life (150 g, mixed in water)	hrs:min	-	08:30	-	-	Tecam Gel Time
Earliest Time To Apply Vacuum	hrs:min	-	07:10	-	-	Internal Gurit Method
Latest Time To Apply Vacuum	hrs:min	-	09:10	-	-	Internal Gurit Method
Earliest Demould Time	hrs:min	-	60:00	-	-	Internal Gurit Method

### CURED RESIN MECHANICAL AND THERMAL PROPERTIES

PROPERTIES	SYMBOL	UNITS	16 HOURS AT 50°C**	5 HOURS AT 85°C**	TEST STANDARD
Glass Transition Temperature	T <sub>g1</sub>	°C	76	-	ISO 6721 (DMA)
Glass Transition Temperature	T <sub>g2</sub>	°C	72	107	ISO 11357 (DSC)
Ultimate Glass Transition Temp.	UT <sub>g2</sub>	°C	112	-	ISO 11357 (DSC)
Cured Density	ρ <sub>CURED</sub>	g/cm <sup>3</sup>	1.14	-	ISO 1183-1A
Linear Shrinkage	-	%	1.37	-	ISO 1183-1A
Tensile Strength	σ <sub>T</sub>	MPa	72.9	-	ISO 527-2
Tensile Modulus	E <sub>T</sub>	GPa	3.18	-	ISO 527-2
Tensile Strain	ε <sub>T</sub>	%	3.00	-	ISO 527-2

### CURED LAMINATE\*\*\* MECHANICAL PROPERTIES

PROPERTIES	SYMBOL	UNITS	16 HOURS AT 50°C**	TEST STANDARD
Glass Transition Temperature	T <sub>g1</sub>	°C	76	ISO 6721 (DMA)
Cured Ply Thickness	-	mm	0.28	ASTM D792
Fibre Volume Fraction	V <sub>FVF</sub>	%	40-41	ASTM D 3171 Method II
0° Tensile Strength****	X <sub>T</sub>	MPa	418	ISO 527-4
0° Tensile Modulus****	E <sub>t</sub>	GPa	21.3	ISO 527-4
0° Compressive Strength****	X <sub>C</sub>	MPa	424	SACMA SRM1-94
0° Compressive Modulus****	E <sub>c</sub>	GPa	22.6	SACMA SRM1-94
ILSS	X <sub>ILSS</sub>	MPa	54.2	ISO 14130

\*working time properties are highly subjective to ambient conditions and should be used as an approximate guideline for all Ampreg™ systems

\*\*initial cure of 24 hours at 21°C

\*\*\*laminate construction: 10 plies of RE301H8, 50% resin content by weight

\*\*\*\*normalised to 40% fibre volume fraction

## AMPREG™ 31 RESIN & AMPREG™ 3X HIGH TG HARDENER

This 1 page product summary is intended for use in conjunction with further advice provided under the Instructions for Use section. All data has been generated from typical production material and does not constitute a product specification.

### MIXING AND HANDLING

PROPERTY	UNITS	AMPREG™ 31 RESIN	HIGH TG HARDENER	MIXED SYSTEM	TEST METHOD
Colour	-	Yellow	Colourless	Yellow	-
Mix ratio by weight	Parts by weight	100	28	-	-
Mix ratio by volume	Parts by volume	100	29	-	-
Density at 21 °C	g/cm <sup>3</sup>	1.12	0.96	1.08	ISO 1183-1B

### COMPONENT & MIXED SYSTEM PROPERTIES\*

PROPERTY	UNITS	15°C	20°C	25°C	30°C	TEST METHOD
Ampreg™ 30 Resin Viscosity	cP	8900 - 9300	3900 - 4300	2000 - 2800	900 - 1300	-
Ampreg™ 3X High Tg Hardener Viscosity	cP	110	80	60	40	-
Initial Mixed System Viscosity	cP	-	1110	-	-	-
Pot-life (150 g, mixed in water)	hrs:min	-	05:40	-	-	Tecam Gel Time
Earliest Time To Apply Vacuum	hrs:min	-	04:40	-	-	Internal Gurit Method
Latest Time To Apply Vacuum	hrs:min	-	06:40	-	-	Internal Gurit Method
Earliest Demould Time	hrs:min	-	30:00	-	-	Internal Gurit Method

### CURED RESIN MECHANICAL AND THERMAL PROPERTIES

PROPERTIES	SYMBOL	UNITS	16 HOURS AT 50°C**	5 HOURS AT 85°C**	TEST STANDARD
Glass Transition Temperature	T <sub>g1</sub>	°C	77	-	ISO 6721 (DMA)
Glass Transition Temperature	T <sub>g2</sub>	°C	71	100	ISO 11357 (DSC)
Ultimate Glass Transition Temp.	UT <sub>g2</sub>	°C	114	-	ISO 11357 (DSC)
Cured Density	ρ <sub>CURED</sub>	g/cm <sup>3</sup>	1.14	-	ISO 1183-1A
Linear Shrinkage	-	%	1.77	-	ISO 1183-1A
Tensile Strength	σ <sub>T</sub>	MPa	75.6	-	ISO 527-2
Tensile Modulus	E <sub>T</sub>	GPa	3.25	-	ISO 527-2
Tensile Strain	ε <sub>T</sub>	%	6.58	-	ISO 527-2

### CURED LAMINATE\*\*\* MECHANICAL PROPERTIES

PROPERTIES	SYMBOL	UNITS	16 HOURS AT 50°C**	TEST STANDARD
Glass Transition Temperature	T <sub>g1</sub>	°C	77	ISO 6721 (DMA)
Cured Ply Thickness	-	mm	0.31	ASTM D792
Fibre Volume Fraction	V <sub>FVF</sub>	%	36-37	ASTM D 3171 Method II
0° Tensile Strength****	X <sub>T</sub>	MPa	401.4	ISO 527-4
0° Tensile Modulus****	E <sub>T</sub>	GPa	20.9	ISO 527-4
0° Compressive Strength****	X <sub>C</sub>	MPa	342.2	SACMA SRM1-94
0° Compressive Modulus****	E <sub>C</sub>	GPa	-	SACMA SRM1-94
ILSS	X <sub>ILSS</sub>	MPa	43.4	ISO 14130

\*working time properties are highly subjective to ambient conditions and should be used as an approximate guideline for all Ampreg™ systems

\*\*initial cure of 24 hours at 21°C

\*\*\*laminate construction: 10 plies of RE301HB, 50% resin content by weight

\*\*\*\*normalised to 40% fibre volume fraction

## NOTICE

All advice, instruction or recommendation is given in good faith but the selling Gurit entity (the Company) only warrants that advice in writing is given with reasonable skill and care. No further duty or responsibility is accepted by the Company. All advice is given subject to the terms and conditions of sale (the Conditions) which are available on request from the Company or may be viewed at Gurit's Website: [www.gurit.com/terms-and-conditions.aspx](http://www.gurit.com/terms-and-conditions.aspx)

The Company strongly recommends that Customers make test panels in the final process conditions and conduct appropriate testing of any goods or materials supplied by the Company prior to final use to ensure that they are suitable for the Customer's planned application. Such testing should include testing under conditions as close as possible to those to which the final component may be subjected. The Company specifically excludes any warranty of fitness for purpose of the goods other than as set out in writing by the Company. Due to the varied nature of end-use applications, the Company does, in particular, not warrant that the test panels in the final process conditions and/or the final component pass any fire standards.

The Company reserves the right to change specifications and prices without notice and Customers should satisfy themselves that information relied on by the Customer is that which is currently published by the Company on its website. Any queries may be addressed to the Technical Services Department.

Gurit is continuously reviewing and updating literature. Please ensure that you have the current version by contacting your sales contact and quoting the revision number in the bottom left-hand corner of this page.

## TECHNICAL CONTACT INFORMATION

For all other enquiries such as technical queries:

Telephone + 44 1983 828000 (08:30 – 17:00 GMT)  
Email [technical.support@gurit.com](mailto:technical.support@gurit.com)

## 24-HOUR CHEMICAL EMERGENCY NUMBER

For advice on chemical emergencies, spillages, fires or exposures:

Europe +44 1273 289451  
Americas +1 646 844 7309  
APAC +65 3158 1412

**E** [customer.support@gurit.com](mailto:customer.support@gurit.com)

**W** [www.gurit.com](http://www.gurit.com)